

Serial No. 10/646,599

- 2 -

52012sh

CLAIM AMENDMENTS

1. (Currently Amended) In an additive manufacturing process of the type wherein an object is fabricated by consolidating material increments from a feedstock in accordance with a description of the object, a method of preventing the build-up of material in a localized area comprising the step of: providing a feedstock in the form of sheet, tape, or wire material increments; bonding the material increments to an object being fabricated; and treating the object being fabricated, the feedstock, or both, so as to inhibit the consolidation of material increments in one or more localized areas.

2. (Original) The method of claim 1, wherein the treatment affects the surface chemistry of the feedstock to prevent local bonding.

3. (Original) The method of claim 1, wherein the treatment is applied to a previously built surface of the object.

4. (Original) The method of claim 1, wherein the treatment includes the introduction of an oxidizer.

5. (Original) The method of claim 1, wherein the oxidizer is a metal nitrate, chlorate, chromate, peroxide, or manganate.

6. (Original) The method of claim 1, wherein the treatment includes the introduction of a base or alkali.

7. (Original) The method of claim 1, wherein the treatment includes a thin coating of a lubricious material such as tin to prevent the breakup of an oxide layer.

8. (Original) The method of claim 1, wherein the treatment forms a coating having a thickness in

Serial No. 10/646,599

- 3 -

52012sh

the range of angstroms to microns to prevent accumulation of Z-axis errors.

9. (Original) The method of claim 1, wherein the consolidation is in the form of ultrasonic consolidation.

10. (Original) In an additive manufacturing process of the type wherein an object is fabricated by consolidating material increments from a feedstock in accordance with a description of the object, a method of preventing the build-up of material in a particular area comprising the steps of:

analyzing the description of the object to determine if an intrinsic support would be necessary or desirable to the fabrication thereof;

determining whether localized, inhibited consolidation would be appropriate to the formation of the intrinsic support and, if so:

treating the object being fabricated, the feedstock, or both, so as to inhibit the consolidation of material increments in accordance with the description of the object.

11. (Original) The method of claim 10, wherein the treatment affects the surface chemistry of the feedstock to prevent local bonding.

12. (Original) The method of claim 10, wherein the treatment is applied to a previously built surface of the object.

13. (Original) The method of claim 10, wherein the treatment includes the introduction of an oxidizer.

14. (Original) The method of claim 10, wherein the oxidizer is a metal nitrate, chlorate, chromate, peroxide, or manganate.

15. (Original) The method of claim 10, wherein the treatment includes the introduction of a base or alkali.

Serial No. 10/646,599

- 4 -

52012sh

3 BUFFORD, KRASS, GRIFFIN, SPRINKLE, ANDERSON & GITKOWSKI, P.C. 2701 TROY CENTER DR., SUITE 330, P.O. BOX 7021 TROY, MICHIGAN 48067-7021 (248) 647-6003

16. (Original) The method of claim 10, wherein the treatment includes a thin coating of a lubricious material such as tin to prevent the breakup of an oxide layer.

17. (Original) The method of claim 10, wherein the treatment forms a coating having a thickness in the range of angstroms to microns to prevent accumulation of Z-axis errors.

18. (Original) The method of claim 10, wherein the consolidation is in the form of ultrasonic consolidation.